

# COVER GRADES

Grade	Standard	Abrasion mm <sup>3</sup> max.	Breaking Strength N/mm <sup>2</sup> min.	Elongation at Break % min.	Cover Grade Type
M-24	IS:1891: Part 1	450	24	150	General Purpose
N-17	IS:1891: Part 1	400	17	200	General Purpose
HR (T1)	IS:1891 Part 2	350	12.5	150	Heat Resistant
SHR (T2)	IS:1891 Part 2	350	12.5	150	Heat Resistant
SHR	—	350	12	150	Heat Resistant
UHR	—	450	10	150	Heat Resistant
FR	IS 1891: Part 5	400	17	175	Flame Resistant
OR	IS 1891: Part 3	—	12	250	Oil Resistant
IS HYGENIC	IS:1891: Part 4	350	10	200	Hygienic
W	DIN22102	90	18	400	Abrasion Resistant
X	DIN22102	120	25	450	Abrasion Resistant
Y	DIN22102	150	20	400	General Purpose
Z	DIN22102	250	15	350	General Purpose
V	DIN22102	200	15	350	General Purpose
H	ISO15236	120	24	450	Abrasion Resistant
D	ISO15236	100	18	400	Abrasion Resistant
L	ISO15236	200	15	350	General Purpose
K	ISO15236	200	15	350	Heat Resistant
A	AS1332	70	17	400	Abrasion Resistant
E	AS1332	—	14	300	Flame Resistant
F	AS1332	—	14	300	Flame Resistant
M	AS1332	125	24	450	Abrasion Resistant
N	AS1332	200	17	400	General Purpose
S	AS1332	250	14	300	General Purpose
I	RMA	—	17	400	General Purpose
II	RMA	—	14	400	General Purpose
1	ARPM	125	17	400	Abrasion Resistant
2	ARPM	175	14	400	General Purpose